

Silirub+ S1000

Revision: 19/01/2018

Page 1 from 3

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 15 min
Curing speed * (20°C / 65% R.H.)	Ca. 2 mm/24h
Hardness	Ca. 20 ± 5 Shore A
Density	Ca. 1.03 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	25 %
Max. tension (DIN 53504)	1,20 N/mm ²
Elasticity modulus 100% (DIN 53504)	0,30 N/mm ²
Elongation at break (DIN 53504)	> 700 %
Temperature resistance	-60 °C → 180 °C
Application temperature	5 °C → 35 °C

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Product description

Silirub+ S1000 is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties

- Long open time.
- Excellent moisture and mold resistance.
- Impervious to mould
- Very easy to apply
- Colourfast and UV resistant
- Permanently elastic after curing
- Typical acetic smell

Applications

- Building- and construction joints, especially in sanitary and humid places.
- For sealing of joints in sanitary and other moist rooms between e.g.. showers, bathtubs and (tiled) walls, between walls and washbasins, between floors and toilet.
- Top sealing in glazing.

Packaging

Colour: transparent, brilliant white, ivory
Packaging: 310 ml cartridge

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates, ceramic tiles, aluminium, enamel, stainless steel, glass, ... no pvc
Nature: clean, dry, free of dust and grease.
Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. No primer needed for non-porous substrates.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub+ S1000

Revision: 19/01/2018

Page 2 from 3

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult the packaging label for more information.

Remarks

- Because of the acid nature, certain metals (eg copper, lead) can be affected.
- Do not use on natural stones like marble, granite,...(staining). Use Soudal Silirub MA or Silirub+ S8800 for this application.
- Do not use on polycarbonate. Use Silirub PC instead.
- The sanitary formula should not replace regular cleaning of the joint. Excessive contamination, deposits or soap remainigs will stimulate the development of fungi.
- A total absence of UV can cause a color change of the sealant.
- In an acid environment or in a dark room, white silicone can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour.
- We strongly recommend not to apply the product in full sunlight as it will dry very fast.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- Do not use in applications where continuous water immersion is possible.
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Not suitable for bonding aquariums.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

Environmental clauses*Leed regulation:*

Silirub+ S1000 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces al previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub+ S1000

Revision: 19/01/2018

Page 3 from 3

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.